

**Bitumen with penetration Grade of 100/150**

|   | Unit    | Test method                    | Grade   |
|---|---------|--------------------------------|---------|
| Penetration at 25 °C                    | 0.1mm   | EN 1426                        | 100-150 |
| Softening Point                         | °C      | EN 1427                        | 39-47   |
| Resistance to Hardening at 163 °C       |         | EN 12607-1<br>or<br>EN 12607-3 |         |
| Change of Mass Maximum                  | %       |                                | 0.8     |
| Retained Penetration Minimum            | %       |                                | 43      |
| Softening Point after Hardening Minimum | °C      | EN 1427                        | 41      |
| Flash Point Minimum                     | °C      | EN22592                        | 230     |
| Solubility Minimum                      | % (m/m) | EN 12592                       | 99.0    |