

Bitumen with penetration Grade of 160/220

	Unit	Test method	Grade
Penetration at 25 °C	0.1mm	EN 1426	160-220
Softening Point	°C	EN 1427	35-43
Resistance to hardening at 163 °C		EN 12607-1 or EN 12607-3	
Change of Mass Maximum	%		1.0
Retained Penetration Minimum	%		37
Softening Point after Hardening Minimum	°C	EN 1427	37
Flash Point Minimum	°C	EN22592	220
Solubility Minimum	% (m/m)	EN 12592	99.0