

## Cationic Bitumen (Asphalt) Emulsion CMS2

Property	Min	Max	Test Method
<b>Test on Emulsions</b>			
Viscosity, Saybolt Furol at 25 °C, SFS	-	-	ASTM D244
Viscosity, Saybolt Furol at 25 °C, SFS	40	450	ASTM D3143
Storage stability test, 24-h, %	-	1	ASTM D6930
Demulsibility, 35 mL, 0.8 % dioctyl sodium sulfosuccinate, %	-	-	ASTM D6936
<b>Coating ability and water resistance:</b>			
Coating, dry aggregate	good	-	ASTM D244
Coating, after spraying	Fair	-	ASTM D244
Coating, wet aggregate	Fair	-	ASTM D244
Coating, after spraying	Fair	-	ASTM D244
Particle charge test	positive		ASTM D244
Sieve test, %	-	0.1	ASTM D6933
Cement mixing test, %	-	-	ASTM D6935
<b>Distillation:</b>			
Oil distillate, by volume of emulsion, %	-	12	ASTM D6997
Residue, %	65	-	ASTM D244
<b>Tests on residue from distillation test:</b>			
Penetration, 25°C (77°F), 100 g, 5 s	100	250	ASTM D5
Ductility, 25°C (77°F), 5 cm/min, cm	40	-	ASTM D113
Solubility in trichloroethylene, %	97.5	-	ASTM D2042