

Cutback Bitumen (Medium-Curing) with Grade: MC-30

Property	Min	Max	Test Method
Kinematic Viscosity at 60°C mm ² /s	30	60	ASTM D2170
Flash Point (Tag Open-Cup), °C	38	-	ASTM D3143
Distillate Test			
Distillate, Volume Percent of Total Distillate to 360°C			
To 225°C	-	25	ASTM D402
To 260°C	40	70	ASTM D402
To 316°C	75	93	ASTM D402
Residue from distillation to 360°C, percent volume by difference	50	-	ASTM D402
Tests on Residue from Distillation:			
Viscosity at 60 °C,	30	120	ASTM D2170
Penetration at 25 °C,	120	250	ASTM D5
Ductility at 25 °C,	100	-	ASTM D113
Solubility in trichloroethylene, %	99	-	ASTM D2042
Water, %	-	0.2	ASTM D95