

Oxidized Bitumen with Grade 95/25

| Property | Test Method BS 2000 | Grade |
|---|------------------------|-------|
| | | 95/25 |
| Softening point, 8C | Part 58 | 95±5 |
| Penetration at 258C, dmm | Part 49 | 25±5 |
| Loss on heating for 5 h at 1638C, loss by mass %, max | Part 45 | 0.2 |
| Solubility in trichloroethylene, % by mass, min | Part 47 | 99.5 |