

Bitumen with penetration Grade of 40/50

	Unit	Test method	Grade
Penetration at 25 °C	0.1mm	EN 1426	40-50
Softening Point	°C	EN 1427	50-58
Resistance to Hardening at 163 °C		EN 12607-1 or EN 12607-3	
Change of Mass Maximum	%		0.5
Retained Penetration Minimum	%		53
Softening Point after Hardening Minimum	°C	EN 1427	52
Flash Point Minimum	°C	EN22592	240
Solubility Minimum	% (m/m)	EN 12592	99.0