

**Cutback Bitumen (Medium-Curing) with Grade: MC-3000**

Property	Min	Max	Test Method
Kinematic Viscosity at 60°C mm <sup>2</sup> /s	3000	6000	ASTM D2170
Flash Point (Tag Open-Cup),°C	66	-	ASTM D3143
<b>Distillate Test</b>			
<b>Distillate, Volume Percent of Total Distillate to 360°C</b>			
To 225°C	-	-	ASTM D402
To 260°C	-	15	ASTM D402
To 316°C	15	75	ASTM D402
Residue from distillation to 360°C, percent volume by difference	80	-	ASTM D402
<b>Tests on Residue from Distillation:</b>			
Viscosity at 60 °C,	30	120	ASTM D2170
Penetration at 25 °C,	120	250	ASTM D5
Ductility at 25 °C,	100	-	ASTM D113
Solubility in trichloroethylene, %	99	-	ASTM D2042
Water, %	-	0.2	ASTM D95