

### **Oxidized Bitumen with Grade 85/25**

Property	Test Method BS 2000	Grade
		85/25
Softening point, 8C	Part 58	85±5
Penetration at 258C, dmm	Part 49	25±5
Loss on heating for 5 h at 1638C, loss by mass %, max	Part 45	0.2
Solubility in trichloroethylene, % by mass, min	Part 47	99.5